

## Colnatec High Temperature Monitor Crystals

The World's Most Advanced Film Thickness Sensors

### Superior Crystals for Harsh Process Film Thickness Monitoring

The measurement of film thickness during a vacuum deposition process can be accomplished with great accuracy and precision using a quartz crystal microbalance, or QCM. Under controlled conditions, it is possible to achieve Angstrom level resolution of the film thickness. In practice, however, this is rarely achieved.

A film thickness monitor measures the change in resonance frequency of an oscillating quartz crystal while a thin film coating is collecting on its surface. As the coating builds up the resonance frequency decreases in a very predictable fashion. If the density of the deposited film is known, the thickness of the film can be calculated in real-time.

A film thickness monitor, however, works on the underlying assumption that any change in the resonance frequency is solely a result of film build-up. Unfortunately, quartz crystals can also change resonance frequency when exposed to a thermal gradient or mechanical stress. In a typical thin film deposition, both of these phenomena exist due to either the deposition source radiation, highly energetic species (as in sputtering) or stresses caused by film condensation. Often these factors exist in concert.

For processes that operate at temperatures above 100°C, standard quartz crystals are extremely noisy. This noise prevents accurate and stable film thickness measurements. For this reason, Colnatec invented two types of monitor crystals that operate stably above 100°C, are stress insensitive, and can operate in plasmas--the HT™ quartz crystal, good to 300°C, and SuperQuartz™ (SQ™), a revolutionary crystalline material good to 500°C+. Both crystals now enable measurement of ALD, CVD, OVPD, high temperature PVD and thin film furnace processes such as selenization and indiffusion.

As an added benefit, the HT™ crystal will not show a rate spike when the deposition source shutter is opened, or exposed to plasmas. Typically, this action causes a frequency shift of up to 100 Hz, which translates to rate changes of 50 Angstroms or more for films such as aluminum. Further, the noise associated with the intense energy of impinging atoms in sputtering is dramatically reduced, owing to the stress insensitivity of the crystal. These are very real advantages in the measurement of nanometer films used in the manufacture of OLED's, precision optical interference films, or next generation electronic devices (including solar cells).

HT™ and SQ™ crystals can be used in place of standard AT-cut quartz in all commercially available film thickness monitors and controllers, and they are the only materials that will work in Colnatec's self-cleaning and sealed sensor heads. They are available in 5 or 6 MHz versions, with gold, aluminum, or platinum (SQ™ only) electrodes, sized in 14mm (HT™ & SQ™) and 12.5mm (HT™ only) diameters.



**14mm 6MHz HT™ Crystals**

CNT06HTIG: Gold  
CNT06HTIA: Aluminum


Frequency: 5.980-5.990 MHz  
Resistance: < 40 Ohm  
Finish: 9 microns RMS  
Diameter: 14mm  
Contour: Plano-Convex  
Cut: HT cut +/- .5'



**14mm 5MHz HT™ Crystals**

CNT05HTBG: Gold  
CNT05HTBA: Aluminum


Frequency: 4.960-4.975 MHz  
Resistance: < 40 Ohm  
Finish: 9 microns RMS  
Diameter: 14mm  
Contour: Plano-Convex  
Cut: HT cut +/- .5'



**12.5mm 5MHz HT™ Crystals**

CNT05HTSG: Gold  
CNT05HTSA: Aluminum

Frequency: 4.990-5.000 MHz  
Resistance: < 40 Ohm  
Finish: 9 microns RMS  
Diameter: 12.5mm  
Contour: Plano-Convex  
Cut: HT cut +/- .5'



**14mm 6MHz SQ™ Crystals**

CNT06SQG: Gold  
CNT06SQA: Aluminum  
CNT06SQP: Platinum

Frequency: 5.975-5.993 MHz  
Resistance: < 40 Ohm  
Finish: 7 microns RMS  
Diameter: 14mm  
Contour: Plano-Convex

*HT™ crystals packaged 10 pieces per disk  
SQ™ crystals packaged 5 pieces per disk*

+1 480.634.1449 | off  
+1 480.634.4339 | fax  
www.colnatec.com  
sales@colnatec.com